



Paracetamol



TECHNICAL DATA SHEET




Best in class whiteback paperboard delivering on aesthetics and performance

		UNITS	METHOD	TOLERANCE	PARAMETERS										
Substance		GSM	Tappi T - 410	+/- 4%	200	230	250	280	300	320	350	380	400	420	450
Caliper		µM	ISO - 534	+/- 5%	223	263	293	330	362	390	434	475	500	525	565
		pt	ISO-534	+/- 5%	8.8	10.3	11.5	13.0	14.2	15.3	17.1	18.7	19.6	20.6	22.2
MD		mN	Tappi T - 556	+/- 10%	79	108	141	198	248	286	374	463	542	602	674
CD		mN	Tappi T - 556	+/- 10%	34	47	62	89	111	128	169	208	243	272	302
GM		mN	Tappi T - 556	+/- 10%	52	71	93	133	166	191	251	310	363	405	451
				VALUES											
Smoothness : Bendtsen		ml/min	ISO 8791-2	50 max											
Plybond		J/m2	Tappi T-833	150 min											
IGT Dry Pick		m/sec	ISO-3782	1.2 min											
Gloss at 75°		%	Tappi T-480	45 ± 5											
Brightness	Top	%	ISO 2470	79 ± 1											
	Buttom	%	ISO 2470	74 ± 1											
Cobb	Top	g/m2	Tappi T-441	30 - 40											
	Buttom	g/m2	Tappi T-441	35 - 80											
Moisture	200-300 gsm	%	Tappi T-412	6.2 - 7.5											
	300-500 gsm	%	Tappi T-412	7.0 - 8.5											

BOARD STRUCTURE

- DOUBLE COATING
- SURFACE SIZING
- FIRST LAYER
Recovered white fiber pulp
- SECOND LAYER
Recovered White Fiber Pulp
- THIRD LAYER
Rich Mechanical Fiber Pulp
- FOURTH LAYER
Recovered White Fiber Pulp
- SURFACE SIZING
- BOTTOM COATING

BOARD STRUCTURE



NOTE ON MEASUREMENTS

- Test climate 23±1°C and RH 50±5% (as per ISO 187).
- All properties are according to Unit Kondurg's lab measurements
- Tolerances are based on 95% Confidence interval on random sample at mill

CERTIFICATES

- FSC® Certified (FSC® - C106778)
- Quality management ISO 9001
- Environmental management ISO 14001
- Health and safety ISO 45001

APPLICATION



FMCG



Pharma



Publication
Covers



Cultural
& Cards



Garments



Consumer
Electronics

Type your text



DEEVYASHAKTI

Deevyashakti India is a constantly evolving organization in response to customer's changing needs. Therefore, this specification is subject to modification. For the latest information, reach us at marketing@deevyashakti.com.